AUTOMOTIVE CLEAR & BASECOAT REMOVER

DESCRIPTION AND USES

Rust-Oleum® Clear & Base Coat Remover is a fast evaporating solvent blend used to remove clear and base coats in 5 minutes without causing damage to the surface metal.

PRODUCTS

SKU (18 oz. spray)	Description
248878	Clear& Basecoat Remover

PRODUCT APPLICATION

APPLICATION

Mask seams and trim openings as this will prevent bleed-back stripping of new finish. Shake well before using. Hold can in an upright position and point arrow on top of button away from you. Spray at a distance of approximately 10-16" from surface. To avoid sagging on vertical surfaces, use a back and forth motion to apply a generous even coat. Limit work area to one section at a time, such as a hood. Let the remover stand until finish is completely blistered or softened completely, generally in 15 minutes. Remove paint by blowing with shop air, or use a flexible plastic scraper. If repeat applications are required, use extreme caution as over-application may cause damage to the exposed OEM primer. Clean the surface with Rust-Oleum Wax & Tar Remover and wipe dry with a clean cloth. Surface must be dry before applying a new finish.

PRODUCT APPLICATION

NOTE: This product may not be compatible with all surfaces and all conditions surrounding the application. Before applying to any surface, always test product in a small inconspicuous area to ensure no damage will result. This product is not recommended for use on fiberglass, plastics or any other synthetic surface. For best results, apply at temperatures between 65-90°F (18-32°C) and avoid direct sunlight or strong breezes.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

PHYSICAL PROPERTIES

Physical Properties	CLEAR & BASECOAT REMOVER
Composition	Dichloromethane and Methanol
MIR	0.50 Max
Fill Weight	18 ounces
Shelf Life	5 years
Flash Point	156°F (-104°C)
Safety Information	For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.